

CLARA

UNIVERSAL TRANSPARENT SINGLE-SIDED TAPE

- Transparent and discreet, it is invisible when applied to any surface
- Exceptional adhesive strength, effective at both high and low temperatures and in the presence of moisture, for fast and secure application
- Extremely reliable in outdoor applications, UV stable and rain resistant
- Ideal for repair work where an invisible finish is required



SEE-THROUGH

HIGH ADHESION

RESISTANT TO UV RAYS

CODE	liner		B		L		pcs
	[mm]	[in]	[mm]	[in]	[m]	[ft]	
CLARA60	60	2.4	60	2.4	15	49	12

Thickness: 0,27 mm

COMPOSITION:

- 1 support: PE film
- 2 glue: acrylic dispersion without solvents
- 3 reinforcing layer: reinforcing polyester grid
- 4 glue: acrylic dispersion without solvents
- 5 release liner: silicone paper



TECHNICAL DATA

properties	standard	value
thickness	-	0,27 mm
adhesion strength on OSB at 90° after 10 minutes	ISO 29862	4,5 N/10 mm
adhesion strength on OSB at 180° after 10 minutes	EN 29862	10,0 N/10 mm
adhesion strength (average) on membrane in PP after 24 hours ⁽¹⁾	ISO 12316-2	25,0 N/50 mm
shear adhesion strength of the joint on membrane in PP after 24 hours ⁽²⁾	ISO 12317-2	70,0 N/50 mm
watertightness	-	compliant
exposure to weather	-	12 months
resistance to temperature	-	-30/+80 °C
fire resistance rating on plain CLT joint (100 mm) 5 mm joint combined with joint cover board ^(*)	EN 1363-4	EI 90
application temperature ⁽³⁾	-	-10/+35 °C
storage temperature ⁽⁴⁾	-	+10/+35 °C
solvents	-	no

⁽¹⁾Minimum required value according to DTU 31.2 P1-2 (France): 15 N/50 mm.

⁽²⁾Minimum required value according to DTU 31.2 P1-2 (France): 40 N/50 mm.

⁽³⁾On dry support and at a temperature > 0 °C. The absence of condensation or frost on the surface must be guaranteed.

⁽⁴⁾Store the product in a cool, dry place for no more than 6 months.

^(*)For full details and tested configurations, please contact our technical department.

♻️ Waste classification (2014/955/EU): 08 04 10.